

MALLAS DE ALEMANIA VERSEIDAG TECHFAB

VS MONOPRINT POLIESTER

CODIGO PROD.	NRO. MALLA	LIGAMENTO	DIAMETRO HILO	SUPERFICIE ABIERTA	ESPESOR DEL TEJIDO	TENSION MALLA NEW / CM.	ABERTURA DE MALLA
	HILOS / CM	PW , TW	um	%	um		um
PES 13 /215W	13	1:1	215	57	390	32-40	465
PES 21/150 W	21	1:1	150	44	280	32-41	330
PES 25/120 W	25	1:1	120	47	220	32-41	265
PES 32 / 100 W	32	1:1	100	41	155	32-42	209
PES 45 / 80 W	45	1:1	80	40	130	30-41	149
PES 55/ 70 W	55	1:1	70	37	120	30-42	109
PES 61 / 60 W	61	1:1	60	40	95	30-43	90
PES 77 / 48 W	77	1:1	48	38	80	30-44	77
PES 90 / 48 W	90	1:1	40	32	90	30-45	55
PES 100 / 40 W	100	1:1	35	36	65	22-35	57
PES 120 / 35 W	120	1:1	35	33	55	22-32	45
PES 120 / 35 Y	120	1:1	40	33	55	22-32	45
PES 120 / 40 Y	120	1:1	35	26	60	22-35	37
PES 130 / 35 W	130	2:1	35	30	67	22-32	34
PES 140 / 35 W	140	1:1	35	20	53	22-30	31
PES 150 / 30 W	150	1:1	30	23	49	20-28	32
PES 150 / 30 Y	150	1:1	30	23	49	20-28	32
PES 150 / 35 Y	150	2:1	35	22	68	20-30	24
PES 165 / 27 Y	165	1:1	27	25	44	20-26	29
PES 165 / 30 Y	165	2:1	30	24	60	20-30	23
PES 180 / 27 Y	180	1:1	27	20	44	20-26	22
PES 180 / 30 Y	180	2:1	30	17	61	20-30	23